

TECHNICAL DATA SHEET





V202CG1



Method









PRODUCT DESCRIPTION:

Printable film composed of a 70-µm, calendered, polymeric PVC, which is coated with a pressure-sensitive acrylic adhesive. For solvent, eco-solvent, latex and UV inkjet printing. Glossy, transparent surface finish.

FILM FEATURES:

•	Thickness	(Indicative value)
		70 μm

• Total thickness (Indicative value)
245 µm

Total weight
 (Average values) Method
 265 g/m² HEXGSM001

Tensile strength
 (Average values)
 min. 35 N/25 mm
 HEXNFX41021

• Elongation at break (Average values) Method

min. 100 % HEXNFX41021

• Shrinkage 168 hours at 70 °C (158 °F) (Average values) Method

< 0.4 mm HEXRET001

LINER:

Silicone-coated PE paper 145 g/m² with light grey HEXIS print.

· Stable under hygrometric variations.

ADHESIVE PROPERTIES:

(Measured average values at publication of the technical data sheet)

after 20 minutes of application

(Average values)

After 24 hours of application

(Average values)

(Average values)

(Average values)

(Average values)

(Average values)

Initial tack

Release

21 N/25 mm

(Average values)

Method

0.2 N/25 mm

HEXFTM003

The adhesive is resistant to most chemicals (alcohol, diluted acids, oils).

ADHESIVE:

- · Solvent-based acrylic adhesive inhibiting migration of plasticisers.
- · Adhesion is immediate and permanent (non-repositionable adhesive), suitable for wet application.

PRINTING GUIDE:

- · Touch-dry after less than 15 minutes depending on the printer used.
- Optimal drying time for the inks before laminating, coating or further processing is 24 hours.

USER'S INSTRUCTIONS:

- Recommended minimum application temperature: +10 °C (+50 °F)
- Operating temperature range: -40 °C to +90 °C (-40 °F to +194 °F)
- · Adhesion to glass, steel, aluminium, PVC, melamine, etc. except grain substrates or substrates coated with acrylic paint.
- In the case of an already painted substrate, apply to undamaged original paintwork only. If the paintwork is not original and/or damaged, the application and the removal are at the judgement and risk of the installer.



TECHNICAL DATA SHEET





OPERATING RECOMMENDATIONS:

- The surface finish of your printings may be modified/improved/protected by applying the appropriate laminate: V750 or PC500. For UV printings, use the protective VCR750 laminate.
- For more information on the application method of V202CG1, please refer to its Application Guide available under the «Professionals» heading, in the «Digital printing media" category on our website www.hexis-graphics.com.

STORAGE:



Storage period before use

1 vear



Storage temperature

+15 °C to +25 °C (+59 °F to +77 °F)



Relative humidity during storage with relative humidity of 50 %

DURABILITY: CENTRAL EUROPEAN CLIMATE

· Vertical outdoor exposure:

Unprinted: 5 years.

Printed and laminated:

- PC500: 5 years,
- V750: 4 years.
- VCR750: 3 years.

Printed: 2 years.



Storage area

in a dust-free environment



Storage method before use in its original packaging



Orientation of rolls before use

vertically

To find the indicative durabilities of the films for any other exposure and geographical area, please refer to the «Conversion rules for indicative durabilities according to geographical area» chart available under Durability, on the «Professionals» pages on our site www.hexis-graphics.com.

NOTES:

Due to the great variety of substrates and the growing number of new applications, the installer must check the suitability of the medium for each application. The measuring methods for the standards quoted above served as the basis for the development of our own measuring methods, which are available on request. Please feel free to contact us to get the latest instructions in use. All of the published information is based on measurements regularly performed in the laboratory. The published information does not however constitute a binding guarantee. The seller cannot be held liable for indirectly related damages and assumes no liability for claims that are higher than the replacement value of the purchased product. All specifications are subject to potential changes without prior notice. Our specifications are automatically updated on our website www.hexis-graphics.com.